

(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 127 896 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
29.08.2001 Bulletin 2001/35

(51) Int Cl.7: **C08F 2/26**, **C08F 14/26**,
C08F 283/08

(21) Application number: **01103317.2**

(22) Date of filing: **13.02.2001**

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **22.02.2000 IT MI000314**

(71) Applicant: **Ausimont S.p.A.**
20121 Milano (IT)

(72) Inventors:
• **Kapeliouchko, Valery**
15100 Alessandria (IT)
• **Marchese, Enrico**
Quarto Inferiore, Asti (IT)

(74) Representative: **Sama, Daniele, Dr. et al**
Sama Patents,
Via G.B. Morgagni, 2
20129 Milano (IT)

(54) Process for the preparation of aqueous dispersions of fluoropolymers

(57) Process for the preparation of a dispersion based on homopolymers/copolymers of tetrafluoroethylene (TFE), said dispersion having a bimodal or multimodal distribution of the particle diameters, wherein the fraction of small particles is in the range 1.5-35% by weight calculated on the dry product; the ratio between the average diameter of the small particles with respect to the average diameter of the dispersion obtained from the polymerization being in the range 0.02-0.6; said process comprising the following essential steps:

- a) preparation of an aqueous microemulsion comprising fluorinated surfactants and (per)fluoropolyether oils (PFPE);
- b) feeding of the microemulsion into the polymerization reactor;
- c) feeding of at least one fluorinated surfactant.

EP 1 127 896 A1

Description

[0001] The invention relates to a process for the preparation directly from polymerization of fluoropolymers aqueous dispersions, having a multimodal or bimodal distribution of the particle sizes and to the dispersion obtainable by a high conversion preparation process; said dispersions having an average diameter in the range 100 nm-400 nm, preferably 150 nm -300 nm, the fraction of small particles having diameter between 10 and 100 nm is in the range 1.5-35% by weight, preferably 3-25% by weight; the ratio between the average diameter of the small particles with respect to the average diameter of the dispersion obtained from the polymerization being in the range 0.025-0.6.

[0002] In particular the invention relates to a radical polymerization process of tetrafluoroethylene (TFE) and copolymers thereof in aqueous emulsion, using a specific dosage of surfactants of which at least one is a component of a microemulsion.

[0003] From the literature (J.G.Brodnyan, Trans.Soc.Rheology, 12:3 (1968), 357; J.S.Chong, E.B.Christiansen, A. D.Baer, J. Appl. Pol. Sci., v.15 (1971), 2007; P.-L.Kuo, C.-J.Chen, J.Polymer Sci. Pol. Chemistry, 31 (1993), 99; C. Chang, R.L.Powell, J.Rheol.,38 (1994), 85; Emulsion polymerization and emulsion polymers. Ed. A. Lovell, M.S. El-Aasser, J. Wiley & Sons, Chichester, 1997, p. 450) it is known that polymeric latexes with a bimodal distribution of the particle diameters with respect to those with a monomodal distribution have a lower viscosity, the concentration being equal. This allows to obtain latexes having a higher concentration not exceeding a certain viscosity, for example up to 74% by volume with a viscosity lower than 1,000 cP. This leads, for example, to a better capability of the film formation and better tensile properties of the film.

[0004] Lately (F.Chu, J.Guillot, A.Guyot, Colloid. Polym. Sci., 276 (1998), 305; F.Chu, J.Guillot, A.Guyot, J.Applied Polymer Sci., 70 (1998), 2667) it has been shown for the polymers based on styrene, butyl acrylate and methylmethacrylic acid, that latexes with multimodal, in particular trimodal, distributions of the particle diameters, have more advantageous rheological and colloidal properties with respect to bimodal latexes and much more advantageous with respect to monomodal latexes. For example, a latex can be obtained having a solid content up to 80% by volume and minimum viscosity in the case of trimodal distribution of the particle diameters with ratio by weight among large/average/small particles equal to 80/10/10.


[0005] The above mentioned literature and USP 4,657,966, USP 4,385,157, USP 5,668,207 refer to hydrogenated polymer latexes and fluoropolymer latexes are not mentioned.

[0006] In USP 5,576,381 it is described how to obtain PTFE latexes with a bimodal distribution of the particle diameters by mixing a latex having a particle diameter in the range 180 nm -400 nm with another latex having an average diameter in a ratio from 0.3 to 0.7 with respect to the particle diameter of the first latex. The process requires the carrying out of two separate polymerization operations with a subsequent mixing in a specific ratio. This complicates the production process, since it requires the separate production of two types of latex and the increase of the storage volumes. Besides, the latex polymerization process with small particles requires to work at a low polymerization conversion, i.e. with low productivity, and it does not allow to obtain the particles having a diameter lower than 100 nm with the typical conversions of the industrial scale. As operating example the preparation of a latex having an average particle diameter of 100 nm the conversion being 10% by weight, is reported. In this patent it is stated that the fluoropolymer latexes with bimodal distribution of the particle sizes can be obtained by carrying out a polymerization reaction with subsequent additions of a surfactant. No example is reported on this aspect. From the examples, bimodal or multimodal distributions of the particle diameters are not obtained from the polymerization. On the other hand, it is known that subsequent additions of surfactants commonly used for the polymerization of tetrafluoroethylene based fluoropolymers, as for example described in USP 3,009,892 and USP 3,391,099 with the purpose to increase the latex stability and the conversion, do not give bimodal or multimodal distributions of the particle diameters. Experiments carried out by the Applicant (see comparative Examples) have shown that by using during the PTFE polymerization subsequent additions of ammonium perfluorooctanoate or of ammonium salt of perfluoropolyether acid as surfactants, multimodal distributions are not obtained.

[0007] The patent application WO 98/58984 mentions the possibility to obtain fluoropolymer latexes having a bimodal distribution of the particles directly from the polymerization but it is not indicated anyway how this result can be obtained.

[0008] USP 4,864,006 uses a microemulsion based on (per)fluoropolyethers for the polymerization of fluorinated polymers and indicates that all the surfactant necessary for the polymerization is fed into the reactor under the form of microemulsion. Besides, it is indicated that the whole microemulsion must be introduced into the reactor before the starting of the reaction. The amount of the used microemulsion must be higher than 0.05 ml of perfluoropolyether for 1 litre of water. Tests carried out by the Applicant (see comparative Examples) have shown that by operating under the conditions indicated in the patent dispersions with multimodal distributions of the particle diameters are not obtained.

[0009] In USP 4,380,618, USP 5,789,508 and WO 97/08214 for the PTFE polymerization and copolymers thereof surfactants of formula:



wherein M = H, NH₄, Na, Li, K are used. Multimodal distributions of the particle diameters are not obtained (see the Examples).

[0010] In USP 4,038,230 it is described how to obtain large spherical PTFE particles by using a non reactive perfluorinated oil phase, for example perfluorobutane, together with the surfactant. Multimodal distributions of the particle diameters are not reported.

[0011] In USP 3,526,614 in order to obtain a sufficiently large particle diameter, the addition of polyvalent metal salts, such as Zn²⁺, is used. This technique allows to control the final diameter of the PTFE particles, but multimodal distributions of the particle diameters are not reported.

[0012] USP 5,523,346 uses for the PTFE polymerization a microemulsion based on polymerizable unsaturated liquid monomers in order to obtain small PTFE particles. This method does not allow to obtain multimodal distributions of the particle diameters. Besides, it is well known that by operating under these conditions it is extremely dangerous due to the explosiveness of the liquid tetrafluoroethylene.

[0013] In patent application WO 96/22315 a perfluorinated microemulsion is used in order to obtain small particles of thermoprocessable fluoropolymers. Multimodal distributions of the particle diameters are not obtained.

[0014] USP 3,925,292 and USP 5,789,083 relate to a mixture formed by a dispersion of PTFE and by a dispersion of a thermoplastic copolymer of tetrafluoroethylene. In said patents it is neither reported nor described that the obtained single latexes have a multimodal distribution of the particle diameters. It is not indicated that said mixture can be directly obtained from the polymerization process.

[0015] In EP 969,027 in the name of the Applicant, a polymerization process in microemulsion to obtain PTFE particles or PTFE copolymers having a size 5-60 nm, is described. Bimodal distribution is not described.

[0016] The need was felt of a polymerization technique able to give PTFE dispersions having a multimodal distribution as defined below.

[0017] It is therefore an object of the present invention a process for the preparation of a dispersion based on tetrafluoroethylene (TFE) homopolymers, or based on copolymers thereof with one or more monomers containing at least one unsaturation of ethylene type in amounts from 0 up to 10% by moles, preferably from 0 to 2% by moles; said dispersion having a multimodal or bimodal, preferably bimodal, distribution of the particle diameters, the dispersion having an average diameter in the range 100 nm-400 nm, preferably 150 nm-300 nm, the fraction of the small particles having diameter between 10 and 100 nm being in the range 1.5-35% by weight calculated on the dry product, preferably 3-25% by weight;

the ratio between the average diameter of the small particles with respect to the average diameter of the dispersion obtained from the polymerization being in the range 0.025-0.6;

said process comprising:

- a) preparation of an aqueous microemulsion comprising fluorinated surfactants and (per)fluoropolyether (PFPE) oils having non reactive, preferably (per)fluorinated, end groups, optionally containing 1 or more H and/or Cl atoms instead of fluorine;
- b) feeding of the microemulsion into the polymerization reactor before the beginning of the polymerization or when polymerization has started;
- c) feeding of at least one fluorinated, preferably perfluorinated, surfactant into the reactor before the starting of the polymerization or when polymerization has started;
- d) addition of water (reaction medium) into the reactor, reactor pressurization with gaseous TFE, optional addition of comonomers, chain transfer agents, stabilizers;
- e) addition of the initiator, and optionally during the polymerization of further amounts of comonomers, initiators, chain transfer agents;
- f) discharge from the reactor of the polymer latex; before the starting of the reaction at least a part of the b) and/or c) feedings must be carried out.

[0018] With the process of the invention a latex containing a high concentration of polymer, generally higher than 25% by weight, preferably higher than 30% by weight, is obtained.

[0019] The Applicant has surprisingly found that by using a dosage system of at least two surfactants of which one is a component of a microemulsion a) based on (per)fluoropolyethers and the other is a fluorinated surfactant not in microemulsion, PTFE latexes having a multimodal or bimodal distribution of the particle diameters are directly obtained from the polymerization process of the invention.

[0020] The fraction and the diameter of the small particles are obtainable from the supernatant layer of the polymerization latex subjected to ultracentrifugation.

[0021] Preferably the amount of the surfactant fed before the starting of the polymerization must exceed 0.05 grams for litre of water, while the total amount of the fed surfactant is generally in the range 0.3-10 g for litre of water.

[0022] The amount of the fluorinated surfactant in the microemulsion a) is in the range 1-80% by weight, preferably 1-45% by weight, with respect to the total weight of surfactants a)+c).

[0023] The fluorinated surfactant used in step c) is preferably anionic.

[0024] It is possible to check that the granulometric distribution curve of the latex particles has at least two separate peaks (bimodal distribution) by a scanning electronic microscope (SEM) or transmission electronic microscope (TEM) or by an atomic force microscope (AFM). Another method is that to use one or more ultracentrifugations of the polymerization latex.

[0025] The latex discharged from the reactor can be subjected, if desired, to the usual post-treatments in connection with the specific uses. For example, the discharged dispersion can be coagulated to obtain fine powders having the multimodal distribution according to the present invention. The latex concentration, carried out for example by clouding or ultrafiltration, can also be mentioned.

[0026] In order to obtain trimodal or higher distributions of the particles, a fluorinated surfactant c) and the microemulsion a) must be fed into the reactor at different reaction progress degrees. For example a feeding of the microemulsion a) and of the surfactant c) before the starting of the reaction, a further feeding of microemulsion a) when more than 50% of tetrafluoroethylene has reacted.

[0027] The Applicant has found that the various obtained populations of the polymer have different not only the particle diameters, but also some properties, such as molecular weight, crystallinity, etc. can be different.

[0028] For example, by using together with the microemulsion a specific dosage of comonomers, initiators and chain transfer agents, latexes can be obtained which besides containing a fraction of large particles formed by PTFE or modified PTFE, having a sufficiently high molecular weight such as to be not thermoplastic, contain at least one fraction of small particles formed by a thermoplastic fluoropolymer based on TFE, i.e. a fluoropolymer having a viscosity of the melt lower than 10^7 poise, preferably from 10^3 to 10^7 poise. In order to obtain the large particle fraction having a sufficiently high molecular weight, the microemulsion dosage with initiators, comonomers and chain transfer agents must be fed at a reaction progress degree of at least 60%, preferably 80%.



[0029] The results of the invention are particularly surprising since the particle nucleation mechanism in polymerization processes in emulsion or in microemulsion is very complex and it is not clarified. The processes leading to the formation of small and large particles influence each other. It is surprising that by the process of the invention multimodal distributions as above defined are obtained.

[0030] The dispersions obtained by the process of the invention, as such or after post-treatment, can be used for the coating of surfaces of organic and/or inorganic polymers, of metals or ceramics, etc. with the advantage to have a better filming with respect to the dispersions having a monomodal distribution of the particles. Besides, the films obtained from the invention dispersions, show also higher tensile properties with respect to the commercial monomodal dispersions having a diameter in the range 180-400 nm.


[0031] The microemulsions a) used in the process of the present invention are described in USP 4,864,006 and USP 4,990,283, herein incorporated by reference, wherein instead of the indicated non reactive end groups, also hydrofluoropolyethers having one or both end groups containing one H atom, or having one or more chlorine atoms instead of fluorine in the chain end groups, can be used.

[0032] The perfluoropolyether oil phase of the microemulsion a) is present in an amount from 0.002 to 10 ml for litre of water, preferably from 0.01 to 2.5 ml.

[0033] The number average molecular weight of the perfluoropolyethers (PFPE) which can be used for the preparation of the microemulsion a) is in the range 350-8,000, preferably 500-1,000. The perfluoropolyether chain comprises repeating units having at least one of the following structures, statistically placed along the chain:



wherein



R_4 and R_5 , equal to or different from each other, are selected from H, Cl, or perfluoroalkyl from 1 to 4 carbon atoms.

[0034] In particular PFPE can have one of the following structures:

1) $\text{TO}-(\text{CF}_2\text{O})_a-(\text{CF}_2\text{CF}_2\text{O})_b-\text{T}$

with a/b in the range 0.5-2, extremes included, a' and b' being integers such as to give the above indicated molecular weight;

2) $\text{TO}-(\text{C}_3\text{F}_6\text{O})_r-(\text{C}_2\text{F}_4\text{O})_b-(\text{CFXO})_t-\text{T}$

with $r/b = 0.5-2.0$; $(r+b)/t$ is in the range 10-30, b , r and t being integers such as to give the above indicated molecular weight, X has the above indicated meaning;


3) $\text{TO}-(\text{C}_3\text{F}_6\text{O})_{r'}-(\text{CFXO})_{t'}-\text{T}$

t' can be 0;

when t' is different from 0 then $r'/t' = 10-100$, preferably 10-30; r' and t' being integers such as to give the above indicated molecular weight; X has the above indicated meaning;

[0035] In the above indicated formulas:


$-(\text{C}_3\text{F}_6\text{O})-$ can represent units of formula



[0036] The T end groups, equal to or different from each other, are (per) fluoroalkyl groups selected from: $-\text{CF}_3$, $-\text{C}_2\text{F}_5$, $-\text{C}_3\text{F}_7$, $-\text{CF}_2\text{Cl}$, $-\text{C}_2\text{F}_4\text{Cl}$, $-\text{C}_3\text{F}_6\text{Cl}$; optionally one or two F atoms, preferably one, can be replaced by H.


[0037] The indicated fluoropolyethers are obtainable by the well known processes in the prior art, see for example the following patents herein incorporated by reference: USP 3,665,041, 2,242,218, 3,715,378, and EP 239,123.

[0038] PFPEs are commercially known, for example FOMBLIN[®] commercialized by Ausimont. The preferred ones among them are:



wherein n and m are such as to give the above indicated molecular weight values; m/n is in the range 0.01-0.5.

[0039] The fluorinated surfactants used in the present invention can be selected from the following:



wherein $M = \text{H}, \text{NH}_4, \text{Na}, \text{Li}, \text{K}$ and n can range from 1 to 6, T as above defined; m/n is in the range 0.05-0.1



wherein n can range from 4 to 12



wherein $M = \text{H}, \text{NH}_4, \text{Na}, \text{Li}, \text{K}$ and n can range from 2 to 5.

[0040] Preferably the fluorinated surfactants of the microemulsion a) have structure (IA).

[0041] The functionalized fluoropolyethers of structure (IA) are obtained for example according to the processes mentioned in EP 148482, USP 3,810,874. The surfactants of structure (IIA) and (IIIA) are commercial products, for example FLUORADR FC1013, FORAFAC[®] 1033D.

[0042] Comonomers having an ethylene unsaturation which can be used are of both hydrogenated and fluorinated type; among the hydrogenated ones, ethylene, propylene, acrylic monomers, for example methylmethacrylate, (meth) acrylic acid, hydroxyethylene-nacrylate, styrene monomers, such as for example styrene, can be mentioned. Among the fluorinated comonomers it can be mentioned:

- C_3-C_8 perfluoroolefins, such as hexafluoropropene (HFP);
- C_2-C_8 hydrogenated fluoroolefins, such as vinyl fluoride (VF), vinylidene fluoride (VDF), trifluoroethylene, perfluoroalkylethylene $\text{CH}_2=\text{CH}-\text{Rf}$, wherein Rf is a C_1-C_6 perfluoroalkyl, such as hexafluoroisobutene;

- C₂-C₆ chloro- and/or bromo- and/or iodo-fluoroolefins, such as chlorotrifluoroethylene (CTFE) ;
- (per)fluoroalkylvinylethers (PAVE) CF₂=CFORf, wherein Rf is a C₁-C₆ (per)fluoroalkyl, for example CF₃, C₂F₅, C₃F₇;
- (per)fluoro-oxyalkylvinylethers CF₂=CFOX, wherein X is a C₁-C₁₂ alkyl, or a C₁-C₁₂ oxyalkyl, or a C₁-C₁₂ (per)fluoroalkyl having one or more ether groups, for example perfluoro-2-propoxy-propyl;
- fluorodioxoles, preferably perfluorodioxoles.

During the polymerization the typical temperatures and pressures of the TFE polymerization processes are used.

[0043] The present invention will be better illustrated by the following Examples, which have a merely indicative but not limitative purpose of the scope of the invention itself.

EXAMPLES

Characterization

[0044] In Examples 1-13 the properties and the parameters of interest are determined through the analysis and characterization methods herein described.

[0045] The determination of the temperature of the first melting and of the heat of crystallization is carried out by the differential calorimetry method, by using a Perkin Elmer calorimeter of the DSC 7 type. About 10 mg of dried polymer are heated from a temperature of 220°C up to 370°C at a rate of 10°C/min. The temperature corresponding to the peak of the melting endothermic curve is indicated as the temperature of the first melting of the polymer. After 15 minutes at 370°C, the polymer is cooled up to a temperature of 220°C at the rate of 10°C/min. The area subtended from the crystallization esothermic curve is integrated and its value, expressed in cal/g, is indicated as heat of crystallization.

[0046] The average diameter of the particles is measured by an instrument based on the laser light diffusion, specifically on the Photon Correlation Spectroscopy, equipped with Brookhaven correlator model 2030 AT and with an Argon Laser light source having a wave length 514.5 nm by Spectra-Physics. The latex specimens to be subjected to measurement, are suitably diluted by water filtered at 0.2 µm on Millipore filter. The scattering measure is carried out at room temperature and at a 90° angle. The latex particle diameter is obtained by the cumulant methods.

[0047] The polymer content of the latex discharged from the reactor and of the supernatant layer obtained by ultracentrifugation is evaluated by the loss weight at 150°C for 1 hour. In particular about 20 g of latex are weighed in a glass beaker and placed in a stove to dry for 1 hour at 150°C. The content of dry product of the latex is obtained from the formula:

$$\text{Dry product \%} = \text{weight after drying/latex initial weight} \times 100$$

[0048] In order to determine the per cent fraction of the solid separated as a consequence of the ultracentrifugation, one proceeds to normalize the content of the dry product of the supernatant layer after centrifugation with respect to the content of the dry product of the latex before centrifugation, according to the formula:

$$\text{Separated solid \%} = (1 - \text{dry product in the supernatant layer \%} / \text{Dry product in the latex \%}) \times 100$$


[0049] In order to evaluate the granulometry distribution of the primary particles, the latex is subjected to centrifugation at 5,000 rpm for 1 hour, using a Kontron ultracentrifuge Centrikon model H401. The separated supernatant layer is subjected to determination of the polymer content by weight loss and to determination of the average diameter of the primary particles, as previously described. As it has been described in the prior art (F.Chu, C.Graillat, J.Guillot, A. Guyot, Colloid.Pol.Sci, 275 (1997), 986) this method which uses ultracentrifugation with PCS allows a careful determination of the particle fractions in the polydispersed latex and it gives results which are confirmed by other techniques such as the transmission electronic microscopy (TEM), capillary hydrodynamic fractionation (CHDF) or field-flow fractionation (FFF).

[0050] The amorphous index has been determined by IR-spectroscopy according to the Moynihan method (J.Am. Chem.Soc., 1959, 81, 1045) as a ratio of the absorptions A778 and A2365.


$$\text{Amorphous index} = A778/A2365$$

[0051] The absolute specific weight is determined according to ASTM D4895.


[0052] The surfactants which are used in Examples 1-13 are the following:




wherein n can range from 1 to 6, m/n is in the range 0.05-0.1




wherein n can range between 1 and 5, m/n is in the range 0.05-0.1




wherein n can range between 4 and 12



wherein M= H, NH₄, Na, Li, K and n can range between 2 and 5. The oils used in Examples 1-13 are the following:



wherein n can range between 1 and 6, m/n is in the range 0.05-0.1



wherein n can range between 1 and 8.

35 EXAMPLE 1

[0053] 5 parts of an ammonium salt of an acid having the structure (I) with an acidimetric molecular weight 530, 3 parts of a perfluoropolyether having the structure of type (A) and molecular weight of about 700 and 8 parts of water are introduced into a glass beaker. The resulting dispersion is perfectly limpid.

40 [0054] 150 grams of the previous dispersion, equal to 0.49 ml/litre of perfluoropolyether, are added to 32 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 140 grams of paraffin with softening point in the range 52°C-54°C were previously introduced into the reactor. 500 cc of (NH₄)₂S₂O₈ (APS) solution corresponding to 220 mg of APS are fed into the autoclave. The autoclave is maintained under mechanical stirring and is pressurized with TFE up to a pressure of 20 bar at a temperature of 55°C.

45 At this point 500 cc of a (NH₄)₂Fe(SO₄)₂·6H₂O (SdM) solution corresponding to 380 mg of SdM are fed into the autoclave. [0055] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 100°C at a rate equal to 0.7°C/min. During the reaction 56 grams of the aqueous solution containing 100 grams/litre of ammonium perfluorooctanoate are fed into the autoclave. After 80 minutes, the TFE feeding is stopped, when 50 13,100 grams of TFE have reacted, the reactor is evacuated and cooled.

[0056] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 157 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 67% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 78 nm. The measured values show that the obtained dispersion has a bimodal distribution of the particle diameters. By the DSC analysis it results that the average specimen of the Example has a heat of crystallization of 8.8 cal/g., the supernatant phase -9.39 cal/g and the precipitated phase -6.07 cal/g.

55 [0057] By the FT-IR analysis it results that the polymer of the supernatant phase has a value of the amorphous index (Moynihan, 773/2365 cm⁻¹) of 0.12, while that of the precipitated phase is of 0.07.

EXAMPLE 2

[0058] 3 parts of an ammonium salt of an acid having the structure (II) with an acidimetric molecular weight 545, 2 parts of a perfluoropolyether having the structure of type (A) and molecular weight of about 800 and 5 parts of water are introduced into a glass beaker. The resulting dispersion is perfectly limpid in a temperature range from 15°C to 55°C.

[0059] 100 grams of the previous dispersion, equal to 0.35 ml/litre of perfluoropolyether, are added to 32 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 140 grams of paraffin with softening point in the range 52°C-54°C were previously introduced into the reactor. 500 cc of $(\text{NH}_4)_2\text{S}_2\text{O}_8$ (APS) solution corresponding to 220 mg of APS are fed into the autoclave. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 55°C. At this point 500 cc of a $(\text{NH}_4)_2\text{Fe}(\text{SO}_4)_2 \cdot 6\text{H}_2\text{O}$ (SdM) solution corresponding to 380 mg of SdM are fed into the autoclave.

[0060] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 100°C at a rate equal to 0.7°C/min. During the reaction 60 grams of the aqueous solution containing 100 grams/litre of ammonium perfluorooctanoate are fed into the autoclave. After 94 minutes, the TFE feeding is stopped, when 14,800 grams of TFE have reacted, the reactor is evacuated and cooled.

[0061] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 155 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 74.6% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 82 nm. The measured values show that the obtained dispersion has a bimodal distribution of the particle diameters.

[0062] By the DSC analysis it results that the average specimen of the Example has a heat of crystallization of 8.2 cal/g, the supernatant phase -10.4 cal/g and the precipitated phase -7.1 cal/g. On the average specimen the value of the absolute specific weight SSG = 2,171 has been determined which indicates high molecular weight of the obtained polymer.

EXAMPLE 3

[0063] 5 parts of an ammonium salt of an acid having the structure (II) with an acidimetric molecular weight 530, 3 parts of a perfluoropolyether having the structure of type (A) and molecular weight of about 700 and 8 parts of water are introduced into a glass beaker. The resulting dispersion is perfectly limpid.

[0064] 8 grams of the previous dispersion, equal to 0.03 ml/litre of perfluoropolyether, are added to 32 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 11 grams of ammonium perfluorooctanoate and 200 g of paraffin with softening point in the range 52°C-54°C were previously introduced into the reactor. 500 cc of $(\text{NH}_4)_2\text{S}_2\text{O}_8$ (APS) solution and disuccinic peroxide (DSAP) corresponding to 100 mg of APS and 2,000 mg of DSAP are fed into the autoclave. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 55°C. At this point 500 cc of a $(\text{NH}_4)_2\text{Fe}(\text{SO}_4)_2 \cdot 6\text{H}_2\text{O}$ (SdM) solution corresponding to 90 mg of SdM are fed into the autoclave.

[0065] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 86°C at a rate equal to 0.6°C/min. During the reaction 50.5 grams of the aqueous solution containing 100 grams/litre of ammonium perfluorooctanoate are fed into the autoclave. After 109 minutes, the TFE feeding is stopped, when 15,800 grams of TFE have reacted, the reactor is evacuated and cooled.

[0066] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 170 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 95.5% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 65 nm. The measured values show that the obtained dispersion has a bimodal distribution of the particle diameters.

EXAMPLE 4

[0067] 15 grams of the dispersion of Example 3, equal to 0.05 ml/litre of perfluoropolyether, are added to 32 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 12 grams of Forafac 1033D, surfactant having the structure (IV) produced and commercialized by Elf Atochem S.A., 200 g of paraffin with softening point in the range 52°C-54°C were previously introduced into the reactor. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 70°C. At this point 500 cc of a $(\text{NH}_4)_2\text{S}_2\text{O}_8$ (APS) solution and disuccinic peroxide (DSAP) corresponding to 150 mg of APS and 3,000 mg of DSAP are fed into the autoclave.

[0068] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 85°C at a rate equal to 0.33°C/min. During the reaction 50.5 grams of the aqueous solution containing 100 grams/litre of Forafac 1033D are fed into the autoclave. After 120 minutes, the TFE feeding is stopped, when 15,800 grams of TFE have reacted, the reactor is evacuated and cooled.

[0069] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 165 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 97% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 55 nm. The measured values show that the obtained dispersion has a bimodal distribution of the particle diameters.

EXAMPLE 5

[0070] 25 grams of the dispersion of Example 3, equal to 0.08 ml/litre of perfluoropolyether, are added to 32 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 40 grams of ammonium perfluorooctanoate, 200 g of paraffin with softening point in the range 52°C-54°C were previously introduced into the reactor. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 70°C. At this point 500 cc of a $(\text{NH}_4)_2\text{S}_2\text{O}_8$ (APS) solution and disuccinic peroxide (DSAP) corresponding to 150 mg of APS and 3,000 mg of DSAP are fed into the autoclave.

[0071] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 85°C at a rate equal to 0.33°C/min. When 13,000 g of TFE have reacted, 150 g of the microemulsion of Example 3 equal to 0.49 ml/litre of perfluoropolyether are fed into the autoclave, the internal temperature of the autoclave is brought to 92°C. When 13,500 g of TFE have reacted, 28 g of perfluoropropylvinylether (PPVE) are fed into the autoclave. After 100 minutes, the TFE feeding is stopped, when 15,800 grams of TFE have reacted, the reactor is evacuated and cooled.

[0072] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 198 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 95.1% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 58 nm. The measured values show that the obtained dispersion has a bimodal distribution of the particle diameters.

EXAMPLE 6 (comparative)

[0073] 24 grams of the aqueous solution of the ammonium perfluorooctanoate are added to 32 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 140 grams of paraffin with softening point in the range 52°C-54°C were previously introduced into the reactor. 500 cc of a $(\text{NH}_4)_2\text{S}_2\text{O}_8$ (APS) solution corresponding to 220 mg of APS are fed into the autoclave. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 55°C. At this point 500 cc of a $(\text{NH}_4)_2\text{Fe}(\text{SO}_4)_2 \cdot 6\text{H}_2\text{O}$ (SdM) solution corresponding to 380 mg of SdM are fed into the autoclave.

[0074] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 100°C at a rate equal to 0.7°C/min. During the reaction 60 g of the aqueous solution containing 100 grams/litre of ammonium perfluorooctanoate are fed into the autoclave. After 80 minutes, the TFE feeding is stopped, when 17,400 grams of TFE have reacted, the reactor is evacuated and cooled.

[0075] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 200 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 99.8% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 115 nm.

EXAMPLE 7 (comparative)

[0076] 24 grams of an aqueous solution of the ammonium salt of the surfactant having the structure (II) are added to 32 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 140 grams of paraffin with softening point in the range 52°C-54°C were previously introduced into the reactor. 500 cc of a $(\text{NH}_4)_2\text{S}_2\text{O}_8$ (APS) solution corresponding to 220 mg of APS are fed into the autoclave. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 55°C. At this point 500 cc of a $(\text{NH}_4)_2\text{Fe}(\text{SO}_4)_2 \cdot 6\text{H}_2\text{O}$ (SdM) solution corresponding to 380 mg of SdM are fed into the autoclave.

[0077] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased

up to 100°C at a rate equal to 0.7°C/min. During the reaction 60 g of the aqueous solution containing 100 grams/litre of the ammonium salt of the surfactant having the structure (II) are fed into the autoclave. After 80 minutes, the TFE feeding is stopped, when 8,700 grams of TFE have reacted, the reactor is evacuated and cooled.

[0078] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 176 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 99.5% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 177 nm.

EXAMPLE 8 (comparative)

[0079] 4 parts of a sodium salt of an acid having the structure (II) with an acidimetric molecular weight 545, 2 parts of a perfluorocarbon C_8F_{18} and molecular weight of about 438 and 4 parts of water are introduced into a glass beaker. The resulting dispersion is perfectly limpid.

[0080] 325 grams of the previous dispersion, equal to 0.16 ml/litre of perfluorocarbon, are added to 32 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 140 grams of paraffin with softening point in the range 52°C-54°C were previously introduced into the reactor. 500 cc of a $(NH_4)_2S_2O_8$ (APS) solution corresponding to 220 mg of APS are fed into the autoclave. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 55°C. At this point 500 cc of a $(NH_4)_2Fe(SO_4)_2 \cdot 6H_2O$ (SdM) solution corresponding to 380 mg of SdM are fed into the autoclave.

[0081] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 100°C at a rate equal to 0.7°C/min. After 42 minutes, the TFE feeding is stopped, when 11,500 grams of TFE have reacted, the reactor is evacuated and cooled.

[0082] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 186 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 99.8% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 105

EXAMPLE 9 (comparative)

[0083] 75 grams of the dispersion of Example 8, equal to 0.27 ml/litre of perfluorocarbon, are added to 32 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 140 grams of paraffin with softening point in the range 52°C-54°C were previously introduced into the reactor. 500 cc of a $(NH_4)_2S_2O_8$ (APS) solution corresponding to 220 mg of APS are fed into the autoclave. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 55°C. At this point 500 cc of a $(NH_4)_2Fe(SO_4)_2 \cdot 6H_2O$ (SdM) solution corresponding to 380 mg of SdM are fed into the autoclave.

[0084] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 100°C at a rate equal to 0.7°C/min. During the reaction 60 grams of the aqueous solution containing 100 grams/litre of ammonium perfluorooctanoate are fed into the autoclave. After 76 minutes, the TFE feeding is stopped, when 13,900 grams of TFE have reacted, the reactor is evacuated and cooled.

[0085] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 261 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 99.9% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 183.

EXAMPLE 10 (comparative)

[0086] 30 grams of the aqueous solution of ammonium perfluorooctanoate are added to 31 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 140 grams of paraffin with softening point in the range 52°C-54°C and 100 grams of perfluoropropylvinylether (PPVE) were previously introduced into the reactor. 500 cc of a $(NH_4)_2S_2O_8$ (APS) solution corresponding to 1000 mg of APS are fed into the autoclave. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 55°C. At this point 500 cc of a $(NH_4)_2Fe(SO_4)_2 \cdot 6H_2O$ (SdM) solution corresponding to 1,450 mg of SdM are fed into the autoclave.

[0087] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 75°C at a rate equal to 0.7°C/min. After 27 minutes, the TFE feeding is stopped, when 3,500 grams of TFE have reacted, the reactor is evacuated and cooled.

[0088] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 115 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 92% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 85 nm.

5 EXAMPLE 11 (comparative)

[0089] 160 grams of the microemulsion of Example 3, equal to 0.52 ml/litre of perfluoropolyether are added to 32 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 100 grams of perfluoromethylvinylether (PMVE) were previously introduced into the reactor. 500 cc of a $(\text{NH}_4)_2\text{S}_2\text{O}_8$ (APS) solution corresponding to 1,600 mg of APS are fed into the autoclave. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 30°C. At this point 500 cc of a $(\text{NH}_4)_2\text{Fe}(\text{SO}_4)_2 \cdot 6\text{H}_2\text{O}$ (SdM) solution corresponding to 480 mg of SdM are fed into the autoclave.

[0090] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 60°C at a rate equal to 0.7°C/min. After 36 minutes, the TFE feeding is stopped, when 7,900 grams of TFE have reacted, the reactor is evacuated and cooled.

[0091] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 83 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 28.3% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 79 nm.

20 EXAMPLE 12 (comparative)

[0092] 140 grams of the microemulsion of Example 3, equal to 0.44 ml/litre of perfluoropolyether are added to 30 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 140 grams of paraffin with softening point in the range 52°C-54°C were previously introduced into the reactor. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 80°C. At this point 500 cc of a $(\text{NH}_4)_2\text{S}_2\text{O}_8$ (APS) solution corresponding to 2,500 mg of APS are fed into the autoclave.

[0093] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 100°C at a rate equal to 1.0°C/min. After 25 minutes, the TFE feeding is stopped, when 13,500 grams of TFE have reacted, the reactor is evacuated and cooled.

[0094] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 90 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 31% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 69 nm.

EXAMPLE 13 (comparative)

[0095] 3 parts of an ammonium salt of an acid having the structure (II) with an acidimetric molecular weight 545, 2 parts of a perfluoropolyether having the structure of type (A) and molecular weight of about 800 and 5 parts of water are introduced into a glass beaker. The resulting dispersion is perfectly limpid.

[0096] 433 grams of the previous dispersion, equal to 1.55 ml/litre of perfluoropolyether, are added to 30 litres of carefully degassed water in a 50 litres autoclave equipped with a mechanical stirrer and previously put under vacuum. Also 140 grams of paraffin with softening point in the range 52°C-54°C were previously introduced into the reactor. 500 cc of a $(\text{NH}_4)_2\text{S}_2\text{O}_8$ (APS) solution corresponding to 220 mg of APS are fed into the autoclave. The autoclave is maintained under mechanical stirring and it is pressurized with TFE up to a pressure of 20 bar at a temperature of 55°C. At this point 500 cc of a $(\text{NH}_4)_2\text{Fe}(\text{SO}_4)_2 \cdot 6\text{H}_2\text{O}$ (SdM) solution corresponding to 380 mg of SdM are fed into the autoclave.

[0097] When the pressure in the reactor has decreased of 0.5 bar, one starts to feed TFE by a compressor so as to maintain a constant pressure of 20 bar inside the reactor. Meanwhile the internal temperature of the reactor is increased up to 100°C at a rate equal to 0.75°C/min. After 45 minutes, the TFE feeding is stopped, when 14,700 grams of TFE have reacted, the reactor is evacuated and cooled.

[0098] The diameter of the polymer primary particles measured by Laser Light Scattering (LLS) is equal to 115 nm. After ultracentrifugation at 5,000 rpm for 1 hour, an amount of solid equal to 44.5% by weight of the total weight is separated and the LLS measure on the supernatant phase gives a value of 88 nm.

TABLE 1

Example	Microemulsion				Other surfactant			Initiators			Comonomer	
	Surfactant		Oil		Type	Initial feeding g/l H ₂ O	Feeding under reaction g/l H ₂ O	APS mg	DSAP mg	SDM mg	Type	Amount g
	Type	Amount g/l H ₂ O	Type	Amount ml/l H ₂ O								
1	I	1.43	A	0.49	III	0	1.75	220	-	380	-	
2	II	0.75	A	0.35	III	0	1.87	220	-	380	-	
3	II	0.08	A	0.03	III	0.344	1.57	100	2000	90	-	
4	II	0.14	A	0.05	IV	0.375	1.57	150	3000	-	-	
5	II	0.14	A	0.05	III	1.375	-	150	3000	-	PPVE	28
6 comp.	-	-	-	-	III	0.75	1.87	220	-	380	-	
7 comp.	-	-	-	-	II	0.75	1.87	220	-	380	-	
8 comp.	II	4.06	B	1.16	-	-	-	220	-	380	-	
9 comp.	II	4.06	B	0.27	III	0	1.87	220	-	380	-	
10 comp.	-	-	-	-	III	0.968	-	1000	-	1450	PPVE	100
11 comp.	II	1.5	A	0.52	-	-	-	1600	-	480	PPVE	56
12 comp.	II	1.42	A	0.44	-	-	-	2500	-	-	-	
13 comp.	II	4.33	A	1.55	-	-	-	220	-	380	-	

TABLE 2

Example	Latex concentration (% by wt.)	C ₂ F ₄ conversion (Kg)	Average diameter (nm)	5000 RPM		
				Supernatant (%)	Dp supernat. (nm)	Dp supern./ average Dp
1	28.4	13.1	157	33	78	0.49
2	31.0	14.8	155	25.4	82	0.53
3	32.4	15.8	170	4.5	65	0.38
4	32.4	15.8	165	3.1	55	0.33
5	32.4	15.8	198	4.9	58	0.29
6 comp.	34.5	17.4	210	0.2	115	0.55
7 comp.	20.9	8.7	176	0.5	177	1.01
8 comp.	25.8	11.5	186	0.2	105	0.56
9 comp.	29.6	13.9	261	0.1	183	0.70
10 comp.	9.9	3.5	115	8	85	0.74
11 comp.	19.3	7.9	83	71.7	79	0.95
12 comp.	30.3	13.5	90	69	69	0.77
13 comp.	32.2	14.7	115	55.5	88	0.77



Claims

1. A process for the preparation of a dispersion based on tetrafluoroethylene (TFE) homopolymers, or based on copolymers thereof with one or more monomers containing at least one unsaturation of ethylene type in amounts from 0 up to 10% by moles, preferably from 0 to 2% by moles, said dispersion having a multimodal or bimodal, preferably bimodal, distribution of the particle diameters, the dispersion having an average diameter in the range

100 nm-400 nm, preferably 150 nm-300 nm, the fraction of small particles having diameter between 10 and 100 nm is in the range 1.5-35% by weight calculated on the dry product, preferably 3-25% by weight; the ratio between the average diameter of the small particles with respect to the average diameter of the dispersion obtained from the polymerization being in the range 0.025-0.6;
 5 said process comprising:

- a) preparation of an aqueous microemulsion comprising fluorinated surfactants and (per)fluoropolyether (PFPE) oils having non reactive, preferably (per)fluorinated, end groups, optionally containing 1 or more H and/or Cl atoms instead of fluorine;
- 10 b) feeding of the microemulsion into the polymerization reactor before the beginning of the polymerization or when polymerization has started;
- c) feeding of at least one fluorinated, preferably perfluorinated, surfactant into the reactor before the starting of the polymerization or when polymerization has started;
- 15 d) addition of water (reaction medium) into the reactor, reactor pressurization with gaseous TFE, optional addition of comonomers, chain transfer agents, stabilizers;
- e) addition of the initiator, and optionally during the polymerization of further amounts of comonomers, initiators, chain transfer agents;
- f) discharge from the reactor of the polymer latex; before the beginning of the reaction at least a part of the b) and/or c) feedings must be carried out.


- 20 2. A process according to claim 1, wherein the amount of the surfactant fed before polymerization starts is higher than 0.05 grams for litre of water, the total amount of the fed surfactant being in the range 0.3-10 g for litre of water.
- 25 3. A process according to claims 1-2; wherein the amount of the fluorinated surfactant in the microemulsion a) is in the range 1-80% by weight, preferably 1-45% by weight, with respect to the total weight of surfactants a)+c).
4. A process according to claims 1-3, wherein in order to obtain trimodal or higher distributions of the particles, a fluorinated surfactant c) and the microemulsion a) are fed into the reactor at different reaction progress degrees, preferably a feeding of the microemulsion a) and of the surfactant c) before the beginning of the reaction, a further feeding of microemulsion a) when more than 50% of tetrafluoroethylene has reacted.
- 30 5. A process according to claims 1-4, wherein the perfluoropolyether oil phase of the microemulsion a) is present in an amount from 0.002 to 10 ml for litre of water, preferably from 0.01 to 2.5 ml.
- 35 6. A process according to claims 1-5, wherein the number average molecular weight of the perfluoropolyethers (PFPE) of the microemulsion a) is in the range 350-8,000, preferably 500-1,000, the perfluoropolyether chain comprises repeating units having at least one of the following structures, statistically placed along the chain:




45 wherein X = F, CF₃;

R₄ and R₅, equal to or different from each other, are selected from H, Cl, or perfluoroalkyl from 1 to 4 carbon atoms.


7. A process according to claim 6, wherein PFPE is selected from the following structures:



with a'/b' in the range 0.5-2, extremes included, a' and b' being integers such as to give the above indicated molecular weight;



with $r/b = 0.5-2.0$; $(r+b)/t$ is in the range 10-30, b, r and t being integers such as to give the above indicated molecular weight, X has the above indicated meaning;




t' can be 0;

when t' is different from 0 then $r'/t' = 10-100$, preferably 10-30; r' and t' being integers such as to give the above indicated molecular weight; X has the above indicated meaning;

the T end groups, equal to or different from each other, are (per)fluoroalkyl groups selected from: $-\text{CF}_3$, $-\text{C}_2\text{F}_5$, $-\text{C}_3\text{F}_7$, $-\text{CF}_2\text{Cl}$, $-\text{C}_2\text{F}_4\text{Cl}$, $-\text{C}_3\text{F}_6\text{Cl}$; optionally one or two F atoms, preferably one, can be replaced by H.

8. A process according to claim 7, wherein the PFPE has the structure:



wherein n and m are such as to give the above indicated molecular weight values; m/n is in the range 0.01-0.5.

9. A process according to claims 1-8, wherein the fluorinated surfactants are selected from the following:



wherein $M = \text{H}, \text{NH}_4, \text{Na}, \text{Li}, \text{K}$ and n ranges from 1 to 6, T is as above defined; m/n is in the range 0.05-0.1



wherein n ranges from 4 to 12.



wherein $M = \text{H}, \text{NH}_4, \text{Na}, \text{Li}, \text{K}$ and n ranges from 2 to 5.

10. A process according to claim 9, wherein the fluorinated surfactants of the microemulsion a) have structure (IA).

11. A process according to claims 1-10, wherein the comonomers having an ethylene unsaturation are of both hydrogenated and fluorinated type:

12. A process according to claim 11, wherein the fluorinated comonomers are selected from:

- C_3-C_8 perfluoroolefins, such as hexafluoropropene (HFP);
- C_2-C_8 hydrogenated fluoroolefins, such as vinyl fluoride (VF), vinylidene fluoride (VDF), trifluoroethylene, perfluoroalkylethylene $\text{CH}_2=\text{CH}-\text{Rf}$, wherein Rf is a C_1-C_6 perfluoroalkyl, such as hexafluoroisobutene;
- C_2-C_6 chloro- and/or bromo- and/or iodo-fluoroolefins, such as chlorotrifluoroethylene (CTFE);
- (per)fluoroalkylvinylethers (PAVE) $\text{CF}_2=\text{CFORf}$, wherein Rf is a C_1-C_6 (per)fluoroalkyl, for example CF_3 , C_2F_5 , C_3F_7 ;
- (per)fluoro-oxyalkylvinylethers $\text{CF}_2=\text{CFOX}$, wherein X is a C_1-C_{12} alkyl, or a C_1-C_{12} oxyalkyl, or a C_1-C_{12} (per)fluoroalkyl having one or more ether groups, for example perfluoro-2-propoxy-propyl;
- fluorodioxoles, preferably perfluorodioxoles.

13. A process according to claim 12, wherein the fluorinated comonomers are selected from:

- hexafluoropropene (HFP);
- chlorotrifluoroethylene (CTFE);

EP 1 127 896 A1

- (per)fluoroalkylvinylethers (PAVE) $\text{CF}_2=\text{CFORf}$, wherein Rf is a $\text{C}_1\text{-C}_3$ (per)fluoroalkyl;
- perfluorodioxoles.

5

10

15

20

25

30

35

40

45

50

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 10 3317

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A,D	WO 98 58984 A (DYNEON GMBH ;BLAEDEL HERMANN (DE); GROSSMANN GERD (DE); LOEHR GERN) 30 December 1998 (1998-12-30) * page 4, line 9 - line 18; claim 11 *	1-13	C08F2/26 C08F14/26 C08F283/08
A,D	EP 0 969 027 A (AUSIMONT SPA) 5 January 2000 (2000-01-05) Examples 9 (comparative), 11, 13	1-13	
A	EP 0 617 058 A (AUSIMONT SPA) 28 September 1994 (1994-09-28) * the whole document *	1-13	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C08F
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 8 June 2001	Examiner Iraegui Retolaza, E
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons Δ : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/92 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 10 3317

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-06-2001

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9858984	A	30-12-1998	DE 19726802 C	10-06-1998
			AU 8338498 A	04-01-1999
			BG 104063 A	31-08-2000
			BR 9810327 A	05-09-2000
			CN 1261385 T	26-07-2000
			EP 0990009 A	05-04-2000
			ZA 9805451 A	06-01-1999
EP 0969027	A	05-01-2000	IT MI981519 A	03-01-2000
			JP 2000034309 A	02-02-2000
EP 0617058	A	28-09-1994	IT MI930551 A	23-09-1994
			AT 158310 T	15-10-1997
			CA 2119411 A	24-09-1994
			DE 69405618 D	23-10-1997
			DE 69405618 T	23-04-1998
			ES 2108313 T	16-12-1997
			JP 7090008 A	04-04-1995
			US 5516863 A	14-05-1996

EPO FORM P4458

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82